IMDS available on request

DEFENSOR-Flex®

The DEFENSOR-Flex® VS01 [Venting Shield] consists of a customer-oriented tailor-made combination of high-tech finishings on fabrics. It protects adjacent cells against particles and gas emerging during the venting of a battery cell. It functions as a seal with a predetermined breaking point.

According to WHO guidelines, the fibres used are considered harmless to health as they are not respirable with a diameter of \geq 6 μ m.

DEFENSOR-Flex® VS01 can be delivered in rolls or customized as make-to-order-product, designed to functional requirements. It is also available with partial pressure sensitive adhesive as mounting aid.

Application of DEFENSOR-Flex® VS01:

- Seal between battery cell and rupture disc
- Predetermined breaking point to protect against particles and gas emerging during the venting of a battery cell.
- DEFENSOR-Flex® VS01 offers a high technical cleanliness and at the same time a high dielectric strength >1kV due to special coatings.
- A particular feature is the shutter thickness of <0.5mm and at the same time high temperature resistance.
- Protection of neighboring cells from venting gases



DEFENSOR-Flex® VS01

VS01 774 0E.....-35

The state of the s	The state of the s	
_functional layers		one
width [mm]		max 1.000
construction	- 11111	unbalanced
THERMO-E-Glass fabric with		E-Glass
functional two-step finish		
operating temperature [°C]		-40 to 500
total area weight [g/sqm]		450
thickness [mm]		0,40
Carlotte Color		Contract of the Contract of th

Tensile strength

warp / weft [N/5cm] ISO 4606 >3.000/>2.000

REACH / RoHS

Thermal conductivity acc. DIN FN 1094

acc. Direct 105		The second second	The second secon	TOP A CONTRACTOR OF THE PARTY OF	The second secon	14 10 10 10 10 10 10 10 10 10 10 10 10 10
t in °C	50	100	200	300	400	500
λ W/(m*K)	0,071	0,076	0,087	0,097	0,106	0,116

compliant








Figure 3 - Side facing the cell

DEFENSOR-Flex®



TRUST THE EXPERTS | HKO

H.K.O. Isolier- und Textiltechnik GmbH

Zum Eisenhammer 54 • 46049 Oberhausen • Germany Phone: +49 208 85994 0 • Fax: +49 208 85994 70 E-Mail: hko@saint-gobain.com • www.hko.de

Remark

This technical information sheet comprises technical specifications and product information according to the state of the art at the time of printing; it will lose validity on publication of a reprint. The technical data sheet applies in connection with other documents of HKO. The technical data of the product may be changed without prior notice. HKO reserves the right to make alterations of the technical data and the materials herein without prior notice in order to keep up with engineering progress and new developments. All technical information and recommendations are based on previous experience and are given after careful review. Due to the variety of influences during processing and application, these pieces of information/recommendations do not release the use from the obligation of own examinations and tests. The technical values are not intended for compiling specifications. The data and explanations in the technical data sheets of HKO in connection with this print do not constitute an acceptance of guarantee. Proposals for application are no assurance of the suitability for the recommended purpose and do not release the user from checking possible infringements of rights of third parties.

